

CLAIMS

1. An electrolytic mixture for molten carbonate fuel cells (MCFC) comprising a carrier solution and a carbonates mixture, characterised in that said carrier solution is a mixture of one or more organic solvents and water.

2. The electrolytic mixture according to claim 1 wherein said carbonates are mixed in such stoichiometric ratios as to obtain the $\text{Li}_2\text{CO}_3/\text{K}_2\text{CO}_3$ eutectic mixture in a ratio of 62/38.

3. The electrolytic mixture according to claims 1 or 2 wherein Li_2CO_3 and K_2CO_3 are mixed in a stoichiometric ratio comprised of between 3:1 and 1:1, preferably in a ratio of 1.7:1.

4. The electrolytic mixture according to any of the claims 1 to 3 wherein said carbonates mixture is constituted by Li_2CO_3 and LiKCO_3 .

5. The electrolytic mixture according to claim 4 wherein LiKCO_3 and Li_2CO_3 are present in a stoichiometric ratio of 3:1.

6. The electrolytic mixture according to any of the claims 1 to 5 wherein said one or more organic solvents are selected from: vaseline, wax or glycerine.

7. The electrolytic mixture according to any of

the claims 1 to 6 wherein said carrier solution is a mixture of glycerine and water, with a glycerine percentage comprised of between 5% and 80% by weight.

8. The electrolytic mixture according to claim 7
5 wherein said carrier solution is a glycerine and water mixture with a glycerine percentage comprised of between 15% and 50% by weight.

9. The electrolytic mixture according to any of
the claims 1 to 8 wherein said carbonates are present in
10 quantities comprised of between 50% and 90% by weight.

10. The electrolytic mixture according to claim 9
wherein said carbonates are present in quantities
comprised of between 70% and 80% by weight.

11. The electrolytic mixture according to any of
15 the claims 1 to 10 in the form of a spreadable paste.

12. A process for the attainment of the
electrolytic mixture according to any of the claims 1 to
11 comprising the steps of:

- a) mixing one or more organic solvents and water;
- 20 b) separately mixing the carbonates;
- c) mixing the carrier solution obtained in step a)
with the carbonates mixture obtained in step b).

13. The process according to claim 12 wherein, in
step a), said one or more solvents are selected from
25 vaseline, wax and/or glycerine, preferably glycerine, and

are used in quantities comprised of between 5% and 80% by weight, preferably comprised of between 15% and 50% by weight.

14. The process according to claims 12 or 13
5 wherein, in step b), the carbonates used are preferably Li_2CO_3 and K_2CO_3 mixed in stoichiometric ratios comprised of between 3:1 and 1:1, preferably 1.7:1.

15. The process according to any of the claims 12 to 14 wherein, in step b), the carbonates are mixed in a
10 ball mill for a period of time comprised of between 10 and 48 hours, preferably between 20 and 28 hours.

16. The process according to any of the claims 12 to 15 wherein, in step c), the carbonates are mixed with the carrier solution in quantities comprised of between
15 50% and 90%, preferably 70% and 80%.

17. The process according to any of the claims 12 to 16 wherein step c) occurs by the gradual addition of the carbonates mixture into the carrier solution with constant mixing.

20 18. A current collector comprising a layer of electrolytic mixture, according to any of the claims 1 to 17, spread over at least one of its surfaces.

19. A collector preparation method comprising the stages of:

25 a) spreading the electrolytic mixture over at

least one of its surfaces;

b) placing said collector on the electrode using a surface not covered by said electrolytic mixture.

20. The method according to claim 19 wherein step
5 a) takes place at room temperature.

21. A molten carbonate fuel cell (MCFC) comprising the current collector according to claim 18.